

Cost-Effective Alternative to Conventional Polyether and Polyester Polyols

INVISTA's TERRIN™ 168G polyol is a 100% aliphatic polyester polyol containing a minimum of 50% recycled content.⁽¹⁾ Due to its unique structure, TERRIN™ 168G polyol is an easily handled, low-viscosity liquid at room temperature and remains a pourable liquid at -15°C/5°F and below.⁽²⁾ It does not crystallize, but exhibits T_g at approximately -70°C.

TERRIN™ 168G polyol can be used in lieu of or in combination with polyether or polyester polyols to formulate a variety of polyurethane products. The resulting polyurethanes can be designed to be soft and flexible - or hard and stiff.

FEATURES AND BENEFITS

- Cost competitive in comparison to conventional polyols
- Have similar hydroxyl values to castor oil, and can be substituted on a nearly equal weight basis
- Supply of TERRIN™ polyols is not dependent on weather and planting cycles
- REACH and TSCA compliant

POLYURETHANES FROM TERRIN™ 168G POLYOL

Formulation (105 isocyanate index)	T_g , °C	Hardness
One shot using PMDI ⁽³⁾	33	35 Shore D
One shot using PMDI, of 88% polyol and 12% triethanolamine ⁽³⁾	68	81 Shore D

SPECIFICATIONS AND TYPICAL PROPERTIES

Hydroxyl number	160-180 mg KOH/g ⁽⁴⁾
Acid number	1.5 max mg KOH/g ⁽⁴⁾
Water, weight	0.1 max % ⁽⁴⁾
Density	1.1 g/mL at 23°C typical
Equivalent weight	312-351 g
Hydroxyl type	Primary & Secondary
Viscosity	830 cP at 23°C typical
Average functionality	2.0 typical
Glass transition temp., T_g	-70°C typical
Recycled or renewable content	60% minimum
Color	Brown

(1) As defined by ISO 14021, Section 7.8; preliminary estimate based on small-scale production.

(2) Consult the MSDS for additional information


(3) Rubinate® M from Huntsman Corporation

(4) Property is included in the product specification

VISCOSITY

10°C/50°F	25°C/77°F	38°C/100°F	75°C/167°F
2813 cSt	871 cSt	378 cSt	76 cSt

Viscosity-Temperature Curve



SOLUTION VISCOSITY

Solvent	75% polyol	50% polyol
Toluene	61 cSt	9 cSt
DBE® - LVP ester	145 cSt	31 cSt
Propylene carbonate	152 cSt	33 cSt



www.TERRIN.INVISTA.com

For samples and further information please contact:
1.800.231.0998 | TERRIN@INVISTA.com

This Product Data Sheet contains selected information about a specific INVISTA product, or group of products, and particular uses of the same. It relates only to the identified product and any identified uses, and is based on information available as of the date hereof. Additional information may be needed to evaluate other uses of the product, including use of the product in combination with any materials or in any processes other than those specifically referenced. Information provided herein with respect to any hazards that may be associated with the product is not meant to suggest that use of the product in a given application will necessarily result in any exposure or risk to workers or the general public. This product data sheet does not contain a complete statement of, and does not constitute a representation, warranty or guaranty with regard to, a product's characteristics, uses, QUALITY, merchantability, FITNESS FOR A PARTICULAR PURPOSE, or the suitability, safety, efficacy, hazards or health effects of the product, whether used singularly or in combination with any other product, EXCEPT TO THE EXTENT REQUIRED BY THE RELEVANT LAW AND REGULATIONS. Purchasers and users of the product are responsible for determining that the product is suitable for the intended use and that their workers and the general public are advised of any risks resulting from such use. Nothing contained in this Product Data Sheet shall be construed to modify any of the commercial terms pursuant to which the product was sold by INVISTA including, but not limited to, terms and conditions addressing each party's respective rights and obligations with regard to warranties, remedies and indemnification.

If purchasers and users believe or have reason to believe that the Product Data Sheet or other information provided to them by INVISTA is inaccurate or in any way insufficient for any purpose, they should immediately notify INVISTA of the same, and of the basis for their belief (for example, studies, data, reports of incidents, etc.) so that INVISTA can determine whether modification or supplementation of the Product Data Sheet, or other measures, are appropriate. Failure of purchasers and users to timely provide such notice shall be deemed a waiver by purchasers and users of any and all claims, demands or causes of action, including causes of action based on an alleged failure to warn, for personal injury or damage to the environment or property arising from or attributable to the use of product.

This disclaimer shall be effective to the extent allowed by law. Should any provision be deemed to be ineffective or unenforceable, that provision shall be deemed severed from the disclaimer and the remaining provisions shall continue to have full force and effect.

INVISTA, DBE® and TERRIN™ are trademarks of INVISTA. Copyright© 2014 INVISTA. All rights reserved.