

TERATE® HT 2004

INDUSTRY LEADERSHIP

For more than 40 years, INVISTA has been an innovative leader in the aromatic polyester polyols market. INVISTA's TERATE® brand polyols are used in the production of rigid foams with improved flammability and physical properties, and are backed by expert technical support around the world.

INVISTA offers a comprehensive line of aromatic polyester polyols with a variety of functionalities and equivalent weights. This allows formulation flexibility in achieving the range of physical and flammability properties required of polyurethane and polyisocyanurate foams.

ATTRIBUTES

The innovative chemistry that forms the basis for the TERATE® HT polyols platform retains the TERATE® polyol burn performance in industry flammability testing, forming char with minimal shrinkage and high weight retention, while improving ease of processing during rigid foam production, and adhesion to various substrates commonly used in rigid polyurethane and polyisocyanurate foam products.

TERATE® HT polyols can help reduce flame retardant loadings in polyurethane and polyisocyanurate rigid foam formulations, and can be used as a partial replacement of traditional polyether polyols with minor formulation adjustments. The unique nature of the TERATE® HT series of polyols can afford foam formulators flexibility in their manufacturing processes in order to meet the needs of their customers.

APPLICATIONS


TERATE® HT 2004 polyol is an aromatic polyester polyol formulated for hydrocarbon blown PIR laminate systems; for use in flexible-faced board stock and metal-faced sandwich panels. It has a relatively low hydroxyl number. Aromaticity can help reduce smoke development substantially when the foam is burned, especially when used as a co-polyol in urethane systems.

PROPERTIES


Production Analysis	Specification	Typical
Acid Number, mg KOH/g	0.9-1.9	1.5
Hydroxyl Number, mg KOH/g	185-200	195
Water Content, %	<0.15%	0.06
Viscosity at 25° C	3500-5000	4350
Functionality		2

Contains Flame Retardant Additive

TERATE® HT 2004 Density – Temperature Data



TERATE® HT 2004 Viscosity – Temperature Data





TERATE® HT 2004

STORAGE AND HANDLING

TERATE® HT 2004 polyol is a stable material which can be stored and handled in carbon steel, stainless steel, or fiberglass tanks, or in tanks made from other conventional construction materials.

Storage temperatures should be kept below 60°C (140°F) to maintain product integrity. It is also recommended that storage vessels and process tanks be blanketed with dry air (min. -40°F/C bulb) or nitrogen to prevent uptake of atmospheric moisture.

The information given above is a guideline. Please email TERATE@INVISTA.com for SDS requests.

FOR MORE INFORMATION:

Email us at TERATE@INVISTA.com or call us:

NORTH AMERICA

800-231-0998

EUROPE

+49-69-305-85550

ASIA-PACIFIC

+86-21-63876666-2659

This Product Data Sheet relates only to the identified product and any identified uses. It is based on information available as of July 2014. Additional information may be needed to evaluate other uses of the product, including use of the product in combination with any materials or in any processes other than those specifically referenced. THIS PRODUCT DATA SHEET DOES NOT CONTAIN A COMPLETE STATEMENT OF, AND DOES NOT CONSTITUTE A REPRESENTATION, WARRANTY OR GUARANTY WITH REGARD TO, A PRODUCT'S CHARACTERISTICS, USES, QUALITY, MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR THE SUITABILITY, SAFETY, EFFICACY, HAZARDS OR HEALTH EFFECTS OF THE PRODUCT, WHETHER USED SINGULARLY OR IN COMBINATION WITH ANY OTHER PRODUCT, EXCEPT TO THE EXTENT REQUIRED BY THE RELEVANT LAW AND REGULATIONS. Nothing contained in this Product Data Sheet shall be construed to modify any of the terms under which the product was sold by INVISTA.